

# **BLACKWATER TECHNICAL SERVICES INC.**

7341 Westport Pl Suite 1A, West Palm Beach Fl. 33413

Phone: 561-508-2830 E-mail: Engdep@blackwatertesting.com



**REPORT NO:** BT-SAZ-24-001D **TEST DATE:** 01/30/2024 **REPORT DATE:** 02/08/2024

## **<u>RENDERED TO:</u>** Saban Acikgoz A.S.

Attn: Mr. Günay Açıkgöz. Cerkezkoy OSB 16. Sk No9 Cerkezkoy 59500 Tekirdag Turkey

#### **<u>REPORT ON:</u>** Impact Testing on Safety Glazing Material

- Saban Acikgoz A.S. (Tekirdag, Turkey)
- Test Size: 34" x 76"
- All test specimens were destroyed by test or by our personnel and have been disposed of as trash.

DESCRIPTION OF TYPICAL SPECIMEN: 5/16 (in) 8 (mm) U Tempered Transparent Glass (TTG)

COATING: NO

PATTERN: N/A

WEIGHT OF ONE LITE: 79.3lb

## PATTERN DEPTH CLASSIFICATION: N/A

### TEMPERATURE: 65°F

Specimen # (*/**)	Test Standard	Thickness (inch)	Impact Drop Height (inch)	Center Punch (Yes/No)	Weight of Largest ten particles (grams)	Maximum Weight Permitted (grams)
1 *	ANSI/CPSC (Comp)	0.317	48.00	No	16	139
2 *	ANSI/CPSC (Comp)	0.326	48.00	No	10	139
3 *	ANSI/CPSC (Comp)	0.331	48.00	No	13	139
4 *	ANSI/CPSC (Comp)	0.334	48.00	No	14	139

Testing in accordance with ANSI Z97.1-2015 (R2020); CPSC 16 CFR 1201; & CAN/CGSB 12.1-2022 as indicated

\*=Smooth Side Out/Non-Coated Side Out

\*\*=Rough Side Out/Coated Side Out

All specimens were impacted once from the select drop height unless noted otherwise.


**REMARKS:** Meets the impact requirements of the referenced standards for the size classification listed.

Under Supervision of: Michael Caldwell P.E.

This item has been digitally signed and sealed by Michael

Caldwell, PE, on 02/12/2024. Printed copies of this document are not considered signed and sealed and the signature must be verified on any electronic copies.

In Charge of Tests: Wyatt Sherman, EIT



Reports pertain to the samples tested only and may not be reproduced without permission. Copyright 2024