



BLACKWATER TECHNICAL SERVICES INC.

7341 Westport Pl Suite 1A, West Palm Beach Fl. 33413

Phone: 561-508-2830 E-mail: Engdep@blackwatertesting.com



REPORT NO: BT-SAZ-24-001A

TEST DATE: 01/30/2024

REPORT DATE: 02/08/2024

RENDERED TO: *Saban Acikgoz A.S.*

Attn: Mr. Günay Açıkgoz.
Cerkez koy OSB 16. Sk No9 Cerkez koy 59500 Tekirdag
Turkey

REPORT ON: Impact Testing on Safety Glazing Material

- Saban Acikgoz A.S. (Tekirdag, Turkey)
- Test Size: 34" x 76"
- All test specimens were destroyed by test or by our personnel and have been disposed of as trash.

DESCRIPTION OF TYPICAL SPECIMEN: 1/4 (in) 6 (mm) U Tempered Transparent Glass (TTG)

COATING: NO

PATTERN: N/A

WEIGHT OF ONE LITE: 56.8lb

PATTERN DEPTH CLASSIFICATION: N/A

TEMPERATURE: 65°F

Specimen # (*/**)	Test Standard	Thickness (inch)	Impact Drop Height (inch)	Center Punch (Yes/No)	Weight of Largest ten particles (grams)	Maximum Weight Permitted (grams)
1 *	ANSI/CPSC (Comp)	0.238	48.00	No	13	100
2 *	ANSI/CPSC (Comp)	0.247	48.00	No	37	100
3 *	ANSI/CPSC (Comp)	0.245	48.00	No	15	100
4 *	ANSI/CPSC (Comp)	0.241	48.00	No	27	100

Testing in accordance with ANSI Z97.1-2015 (R2020); CPSC 16 CFR 1201; & CAN/CGSB 12.1-2022 as indicated

*=Smooth Side Out/Non-Coated Side Out

**=Rough Side Out/Coated Side Out


All specimens were impacted once from the select drop height unless noted otherwise.

REMARKS: Meets the impact requirements of the referenced standards for the size classification listed.

Under Supervision of: Michael Caldwell P.E.

In Charge of Tests: Wyatt Sherman, EIT

This item has been digitally signed and sealed by Michael Caldwell, PE, on 02/12/2024. Printed copies of this document are not considered signed and sealed and the signature must be verified on any electronic copies.



Reports pertain to the samples tested only and may not be reproduced without permission. Copyright 2024